



OREGON RULE CO.
We Measure Up, Down, Sideways and in Circles!

P.O. BOX 1752, OREGON CITY, OR 97045
PH: (503) 657-8330 • FAX 655-8040
Web Site: www.oregonrule.com
E-mail: sales@oregonrule.com

SDS - White Opaque Vinyl

Promotional Advertising

White Opaque Vinyl - Permanent

Self-adhesive film is an essential tool for indoor and outdoor promotional advertising, providing the durability, flexibility, and aesthetic quality that open up all kinds of possibilities for grabbing the consumer's attention for the duration of the advertising campaign.

End-Use Applications:
Cooler Graphics
Counter Graphics
Display Graphics
General-Purpose Signage
Interior Signage
Outdoor Signage
Wall Graphics
Window Graphics

For more information on FLEXcon's pressure-sensitive film solutions for Promotional Advertising, contact your local Sales Representative or our Product Branding Business Team at (508) 885-8370.

Product ID #: FLX059984



This image is an example of how FLEXcon products may be used

Product:

FLEXcon® FLEXmark® WP

Benefits:

- 3.5 mil flexible opaque white vinyl provides good opacity for covering up existing graphics
- Film provides good resistance to scuffing, tearing and abrasion
- Printable via UV and solvent screen, UV and solvent inkjet, and UV offset
- HP Latex compatible
- High-performance permanent adhesive bonds well to ABS, acrylic, Formica, aluminum, stainless steel, HDPE, painted metal, styrene, painted non-vinyl wallboard, glass and more
- 90 lb. polycoated layflat release liner for ease of converting

For Inkjet Printing:

- Typical max. ink limit = 250%
- When storing printed graphics, sheeted, stacked or in roll-form, consider leaving an unprinted margin (about 1/4") to allow for potential shrinkage of the film before trimming

Formica is a registered trademark of The Diller Corporation

FLEXcon® FLEXmark® WP

PRODUCT DATA	VALUE	TEST METHOD
Physical Properties		
Thickness (Mils[microns])	Film	3.5 (89) +/- 10%
	Adhesive	0.9-1.0 (23-25) +/- 0.1 (3)
	Liner	6.9 (175) +/- 10%
Dimensional Stability (%)	MD	0.75
	TD	0.75
Adhesion Properties		
Ultimate Peel from	Average	ASTM D 903 (Modified for 72 hour dwell time)
	Oz/In (N/m)	
ABS	62 (682)	
Acrylic Powder Paint	72 (792)	
Aluminum	66 (726)	
Formica	45 (495)	
Glass	64 (704)	
HDPE	33 (363)	
Painted Metal	70 (770)	
Painted Wood	29 (319)	
Plexiglass	69 (759)	
Polycarbonate	69 (759)	
Polypropylene	24 (264)	
Sintra	54 (574)	
Smooth Painted (non-vinyl) Wallboard	48 (528)	
Stainless Steel	70 (770)	
Styrene	59 (649)	
Varnished Wood	40 (440)	
Expected Shear		ASTM D 3654 Method A
		a. 1 hr. dwell
		b. 1 sq. in. surface
		c. 4 lb. load
Room Temp (hours)	15	
Tack (gm/sq cm)	750	ASTM D 2979
Expected Exterior Life	Two years	
Service Temperature Range	-40°F to 176°F (-40°C to 80°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years when stored at 70°F (21°C) and 50% relative humidity	

Product Performance and Suitability

All of the descriptive information, the typical performance data, and recommendations for the use of FLEXcon products shall be used only as a guide and do not reflect the specification or specification range for any particular property of the product. Furnishing such information is merely an attempt to assist you after you have indicated your contemplated use and shall in no event constitute a warranty of any kind by FLEXcon. All purchasers of FLEXcon products shall be responsible for independently determining the suitability of the material for the purpose for which it is purchased. No distributor, salesman, or representative of FLEXcon is authorized to give any warranty, guaranty, or make any representation in addition or contrary to the above.
Last Modified On: 01/22/2018



1 FLEXcon Industrial Park, Spencer, MA 01562-2642, Telephone (508) 885-8370 FAX (508) 885-8399 www.FLEXcon.com