



OREGON RULE CO.
We Measure Up, Down, Sideways and in Circles!

P.O. BOX 1752, OREGON CITY, OR 97045
PH: (503) 657-8330 • FAX 655-8040
Web Site: www.oregonrule.com
E-mail: sales@oregonrule.com

45# CTT ** GPR™ -disc 02/2014 ** 40# liner
Item#: 0041835

Recommended Print Type(s) to Test
Thermal Transfer Papers
Flexo

----- TRIMLESS PROGRAMS -----

Dist. Ctr	Length	Min. Width	Core
Troy, Ohio	5 K	3"	3"
Atlanta	5 K	3"	3"
Chicago	5 K	3"	3"
Los Angeles	5 K	3"	3"

Facestock: **45# CTT**

A premium, coated sheet that has excellent thermal transfer imaging with a wide range of ribbons, and superior flexo printability.

Typical Value

Basis Weight:	45 #/3300 ft ²
Caliper:	3.0 mils
Tensile MD/CD:	27 / 17
Tear MD/CD:	42 / 45 grams
Opacity:	88%
Brightness:	87%

Adhesive: **GPR™ -disc 02/2014**

A general purpose removable adhesive designed to remove cleanly from a wide variety of substrates. It is engineered to give excellent tack with minimal building of adhesion over time from a variety of surfaces. It is appropriate for laser applications.

Coat Weight:	15 #/3300 ft ²
Coat Weight:	22.2 grams/m ²
Caliper:	.6 mils
Adhesion to Stainless Steel, oz. (90° Peel):	10 oz
Loop Tack, oz.:	17 oz
Service Temperature:	-40 to 200 °F
Minimum Application Temperature:	40 °F
Shear (1000g):	40 minutes

Release Liner: **40# liner**

A bleached kraft liner featuring excellent die cutting and stripping characteristics.

Typical Value

Basis Weight:	39.6 #/3000 ft ²
Caliper:	2.5 mils
Tensile MD/CD:	35 / 15 #/inch
Tear MD/CD:	42 / 48 grams
Opacity:	64%

Total Product Caliper: 6.1 mils
Product Basis Weight Per MMSI: 218.02 #
Shelf Life: 12 month(s) when stored at 72° F, 50% RH

*For application recommendations call 877-210-5104
For samples or other questions please call your Sales
Representative.*

Important Notice

These are typical values and should not be considered a specification. Adhesive properties were tested with a film facestock unless denoted with an asterisk(*).

All [trademarks](#) are the property of their respective owners.

All information, recommendations for use, product designations, and descriptive materials about Spinnaker Coating, LLC products are believed to be reliable, but the furnishing of such information, recommendations for use, product designations, and descriptive material is for informational purposes only and does not constitute a warranty of any kind by Spinnaker Coating, LLC. Because of the variety of possible applications for Spinnaker Coating's products and the continuing development of new applications, all Spinnaker Coating, LLC products are sold with the understanding that each purchaser will independently determine the suitability of any product for the purchaser's intended application, converting, and print processes. Spinnaker Coating, LLC will review, and may modify the information contained in this document from time to time and customers should ensure they have the most recent information.

Last Revision: 04/05/2018